

H400 Fibre Filter Media

Filtration Class

Filter Class acc. to ISO 16890	ISO Coarse 50%
Filter Class acc. to EN 779:2012	G4



Operating Conditions

Medium	100% PET – thermal bonding
Colour	White
Thickness (mm)	20
Approx. Weight (g/m²)	200
Width (cm)	210
Fire Rating	DIN 53438-3 F1
Initial Pressure Drop (Pa)	36
Recommended Final Pressure Drop (Pa)	200

Please note:

The values are subject to the usual variations of the nonwoven production process and are subject to change.

